



DATASHEET

CARADOL SP27-25N

URETHANE CHEMICALS FOR SLABSTOCK APPLICATIONS

U318S


Revised July 2020

CARADOL SP27-25N is a suspension of styrene-acrylonitrile copolymer in a propylene oxide/ethylene oxide based polyether polyol. The product is particularly suited to produce High Resilience slabstock foams. CARADOL SP27-25N exhibits an increased resistance towards cold flow in HR slabstock foams. CARADOL SP27-25N is BHT free.


TYPICAL PROPERTIES

PROPERTY	TEST METHOD	UNIT	VALUE
Appearance			White opaque liquid
Hydroxyl value	ASTM D4274D	mg KOH/g	27
Density at 25°C	ASTM D4052	kg/m ³	1.041
Water content	ASTM D4672	% m/m	0.05
Viscosity at 25°C	ASTM D445	mPa.s	1780
Flash point	ASTM D93	°C	200

VISCOSITY/TEMPERATURE CHARACTERISTICS



DENSITY/TEMPERATURE CHARACTERISTICS



The above typical physical properties are published here as a guide to potential users of the product. A sales specification is published separately.

CARADOL SP27-25N

URETHANE CHEMICALS FOR SLABSTOCK APPLICATIONS

TEST METHODS

ASTM standards are published by the American Society for Testing and Materials at www.astm.org. SMS methods (Shell Methods Series) can be obtained through the local Shell company.

STORAGE AND HANDLING

CARADOL SP27-25N is slightly hygroscopic and must be stored under conditions so that contamination with water and absorption of moisture are prevented. Contact with copper, copper alloys or zinc must be avoided.

The storage temperature of CARADOL SP27-25N is not critical, in that there will be no hazardous conditions created by the storage of the product at any ambient temperature likely to be encountered. It should be noted however that a normal storage temperature, ensuring optimum processing conditions when using the product, is between 20°C and 25°C and that storage at low temperatures may result in the product viscosity being too high for transfer from the storage container with the pumps available.

CARADOL SP27-25N is a stable product and its processing performance is not expected to deteriorate significantly with time providing it is stored as below. As good industrial practice however it is recommended that it is not stored for periods longer than 2 years.

Bulk

Tanks should be of stainless steel or of mild steel, free of mill-scale or rust and maintained in a rust-free condition. When desired, the latter can be lined with an epoxide resin paint or zinc silicate paint approved for this service. Small tanks must be fitted with silica gel breathers, inspected and regenerated at regular intervals; large tanks (of volumes greater than 1000 m³) should be fitted for blanketing with dry nitrogen. Heating facilities may be necessary and where this is the case, care should be taken to ensure that heating coil skin temperatures do not exceed 100°C.

Lines should be of stainless steel or mild steel maintained in a rust-free condition. Trace heating may be necessary in cold climates. Hoses should be of polypropylene, stainless steel or wire bound canvas.

Drums

CARADOL SP27-25N should be stored in dry conditions away from direct sources of heat, preferably in the unopened original containers. Opened drums must be reclosed tightly immediately after drawing-off material.

HAZARD IDENTIFICATION

Low order of acute toxicity by the oral or percutaneous routes, neither irritating nor sensitising to the skin. Slightly irritating to the eyes.

This product is not in the 'flammable' range, but will burn.

Before handling the product refer to the Safety Data Sheet.

PRODUCT CODE

U318S

DISCLAIMER

CARADOL is a Shell trade mark.

The expression 'Shell Chemicals' refers to the companies of the Royal Dutch/Shell Group which are engaged in chemical businesses. Each of the companies which make up the Royal Dutch/Shell Group of companies is an independent entity and has its own separate identity.

The information contained in this publication is to the best of our knowledge, true and accurate, but any recommendations or suggestions which may be made are without guarantee, since the conditions of use are beyond our control.

Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

For further information please contact your local sales representative or visit

www.shell.com/chemicals/customer

www.caradol.com

www.shell.com/chemicals/caradol