



DATASHEET

DPG

PO & DERIVATIVES

U1521
Revised May 2016

DPG is a mixture of dipropylene glycol (DPG) isomers. It is a clear, colourless and odourless, hygroscopic liquid, completely soluble in water.

DPG is miscible in all proportions with low molecular weight aliphatic alcohols and ketones. It is slightly to moderately soluble in aromatics hydrocarbon solvents and only slightly miscible with aliphatics hydrocarbon solvents.

Other chemical names for DPG are: Oxydipropanol

(OH)C3H6O-C3H6(OH)

TYPICAL PROPERTIES

PROPERTY	TEST METHOD	UNIT	VALUE
Purity	ASTM E-202	% (m/m)	99.5 min
Colour	ASTM E-202	Pt-Co	10 max
Water	ASTM E-202	% (m/m)	0.1 max
Acidity as Acetic Acid	ASTM E-202	% (m/m)	0.01 max
Iron	ASTM E-202	ppm	1.0 max
Molecular weight		g/mol	134.2
Density		Kg/m ³	1027
Coefficient of cubic expansion		10 ⁻⁴ /°C	7.4
Refractive index			1.4415
Pour point		°C	-47
Boiling point		°C	229-232
Flash point		°C	149
Vapour pressure at 20 °C		Pa	<1
Vapour pressure at 50 °C		Pa	16
Vapour density (air=1)			4.6
Dynamic viscosity		mPa.s	84
Surface tension at 25°C		mN/m	33.55
Specific heat		kJ/kg K	2.107
Latent heat of evaporation		kJ/kg	593.2
Thermal conductivity		W/m K	0.149
Heat of combustion at 25°C		MJ/kg	25.6
Electrical conductivity		µS/m	0.19
Dielectric constant			21

All typical physical properties are at 20°C unless stated otherwise. The above typical physical properties are published here as a guide to potential users of the product. A sales specification is published separately.

Application

Dipropylene Glycol finds its largest application in the plasticizer market, mainly as an dibenzoate. The second large market for DPG is in unsaturated polyester resins. Other applications are in urethane polyols, alkyd resins, functional fluids like de-icer formulations, inks and paints and as a solvent in fragrances and cosmetics.

Test Methods

Copies of copyrighted test methods can be obtained from the issuing organisations:

American Society for Testing and Materials (ASTM): www.astm.org

US Pharmacopoeia Inc (USP): www.usp.org

For routine quality control analyses, local test methods may be applied that are different from those mentioned in this datasheet. Such methods have been validated and can be obtained through your local Shell Chemicals company.

Storage and Handling

Advice on the storage and handling of DPG can be found in the CEFIC "Guidelines for Handling and Distribution of Propylene Glycol USP/EP" which is available at www.cefic.org. DPG must be processed within 12 months of shipment date.

Hazard Identification

Low order of acute toxicity by the oral or percutaneous routes. Slightly irritating to the eyes and skin. This product is not in the 'flammable' range, but will burn. Before handling the product refer to the Safety Data Sheet.

PROPERTY	TEST METHOD	UNIT	VALUE
Flash point (PMCC)	ASTM D93	°C	149
Lower explosive limit in air		% (v/v)	1
Upper explosive limit in air		% (v/v)	3
Auto ignition temperature		°C	260

DISCLAIMER

The expression 'Shell Chemicals' refers to the companies of the Royal Dutch / Shell Group which are engaged in chemical businesses. Each of the companies which make up the Royal Dutch / Shell Group of companies is an independent entity and has its own separate identity.

The information contained in this publication is to the best of our knowledge, true and accurate, but any recommendations or suggestions which may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

