



Shell Chemicals

Cargo Handling Sheet

NEODOL 1

Document Date: 01 January 2021
Revision 11

Cargo Handling Sheets are for the use of vessels chartered on behalf of Shell Chemicals

Product Details

Product Name: NEODOL 1
IMO Product Name: Undecyl Alcohol
Chemical Family: Alcohols
Product Code: V2705

SDS: <http://www.shell.com/business-customers/chemicals/safe-product-handling-and-transportation/safety-data-sheets.html>

Physical Properties

Density: 830 kg/m³ (20 °C / 68 °F)
Dynamic Viscosity: Typical 17 mPa.s (20 °C / 68 °F)
Vapor Pressure: 0.4 (Pa) (25 °C / 77 °F)
Boiling Point: 245 °C / 473 °F
Pour Point: 11 °C / 52 °F
Flash Point: 121 °C / 250 °F
Appearance: Colourless liquid @ 20 °C / 68 °F; Mild odour

Note 1: Physical Properties are for reference only and valid as of date of this revision; see loading terminal for specific properties.

Note 2: Hazard Identification: Combustible, Cat X product, classified as Toxic under IBC 2021. See SDS for full list of hazards and precautions.

Transhipments

Prior to arranging transhipment Charterer must agree to Owner's proposed plan. When arranged by the Owner, Owner must ensure that all transhipment vessels comply with the requirements of this cargo handling sheet.

Marpol Details

Marpol Annex: II
IMO Ship Type: 2
Inland Barge: Double Hull
IMO Pollution Category: X

IBC 16.2.6:	No
IBC 16.2.9:	Yes
Pre-Wash Required:	Yes
Compatibility Group:	USCG compatibility group 21

Cargo Handling Requirements

N2 Purge Cargo Tanks Prior Loading:	Yes, PQ requirement; Max 1000 ppm (0.1%) O ₂ , see Notes below
N2 Blanket Required:	Yes, PQ requirement; Max 1000 ppm (0.1%) O ₂ , see Notes below
Adjacent Space Purge:	No
Loading Temperature Range:	15 - 35 °C / 59 – 95 °F
Transit Temperature Range:	20 - 45 °C / 68 – 113 °F
Discharge Temperature Range:	20 – 45 °C / 68 – 113 °F
Maximum Heating Coil Temperature:	65 °C / 167 °F
Adjacent Maximum Cargo Temperature:	45°C / 113 °F

Note 1: If Nitrogen blanket is in place and Carrier chooses to tranship, carrier must reapply nitrogen blanket on the cargo, both on the discharging and receiving vessel, at their time, risk, and expense.

Note 2: PQ = Product Quality

Note 3: N2 Blanket Guidance:

- a. O₂ level in tanks: Max 1000 ppm (0.1%) O₂; See Regional Requirements
- b. Vessel to maintain a constant nitrogen overpressure of 20 millibars or more during the voyage
- c. DAILY LOG: During the voyage the vessel shall maintain a daily log of the following and the log shall be sent to the Shell Charterers/Planners at the time of discharge
 1. Tank pressure
 2. O₂ level
 3. Tank Temperature

Regional Requirements

Note 1: Short voyages in Europe may only require blanketing, however if the short voyage is part of an international voyage, the short voyage must also have the tanks purged.

Tank Acceptance Requirements

All nominated shipboard cargo handling systems are to be presented clean (residual free), dry, odor free, rust free, with good gaskets, fit to load this cargo.

Maintenance of heating coils is to be verified in the ship's log. If product is to be heated, heating coils are to be confirmed leak free. If product is not heated, heating coils are to be blown clear and dried with N₂, and blanked off.

Stainless Steel or Coated Tanks: Stainless preferred. High baked and medium baked phenolic epoxy coating in good condition may be used if stainless not available.

Note 1: Vessels offered for loading into coated tanks:

- Carrier to verify suitability of coating
- For newly coated tanks, either partially or fully recoated, the tanks must have carried 3 or more cargoes for a total of >90days at >90% full.
- Tank Coating Condition Questionnaire submitted to Charterers for review prior to fixing a coated vessel
- Coated tanks to be in very good condition with minimal blistering or breakdown, < 0.5% total tank area
- All blisters to be scraped to hard coating
- All defects to be noted in Survey Report
- Pipelines and fittings to be stainless steel

Banned Prior Cargo: Styrene or any other product which can polymerize; Phosphoric acid, Sulphuric acid, and Caustic

Wall Wash Required: Yes; all conducted with Methanol except PH test, which uses DI water

Coated Tanks: WWT conducted by cargo surveyor.

Stainless Steel Tanks: verification of shipboard WWT may be accepted if below specs are met. (Send WWT Verification to the responsible Shell Chemicals charterer and present to cargo surveyor and loading master at loading terminal.)

Wall Wash Test:	Specification	Standard
Hydrocarbons	Pass	ASTM D1722
Chlorides	< 3.0 ppm	IMPCA 002-98
Color Test	< 10 Pt/Co Max	ASTM D1209

Additional WWT for Coated Tanks if Prior Cargo is:

Prior Cargo	Wall Wash Test:	Specification	Standard
Acrylate	PPT	> 30 minutes	ASTM D1363
Oils, Waxes, Veg Oils, Fame	NVM	100 ppm	ASTM D1353
Acids, Alkalis	PH Test	6.9 – 7.1	ASTM E70

Link to: [WWT Verification Form](#)

Safety Information and Incident Reporting

Safety Information:

HSSE information can be found in the SDS or e-SDS.

Incident Reporting:

All incidents should be reported in accordance with regulations and charter party requirements.

International Registered Vessels: If an incident occurs call Shell International Trading and Shipping in London on +442079347777.

Jones Act Vessels: call the Shell 24 hr. incident number at +17132412532. The USA National Response Center telephone number is +18004248802.

For additional marine cargo handling advice or information, contact the responsible regional Shell Chemicals Marine Technical Advisor.



Shell Chemical LP

PO Box 4407

Houston

Texas 77210

USA

Tel +1 866 897 4355

Internet <http://www.shell.com/chemicals>

Disclaimer

The information contained in this publication is, to the best of our knowledge, true and accurate, but any recommendations or suggestions that may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

Shell Chemicals

The expression "Shell Chemicals" refers to the companies of the Shell Group of companies that are engaged in the chemical businesses.

Each of the companies that make up the Shell Group of companies is an independent entity and has its own separate identity.