



Shell

Cargo Handling Sheet

Shell GTL Solvent GS 270

Document Date: 31 May 2023
Revision 7

*Cargo Handling Sheets are for the use of vessels
chartered on behalf of Shell*

Product Details

Trade Name: Shell GTL Solvent GS 270
IMO Product Name: Gas Oil (See Cargo Handling Requirement note below)
Chemical Family: Distillates C8 – C26 branched and linear.
Product Code: Q6538, Q6543

SDS: <http://www.shell.com/business-customers/chemicals/safe-product-handling-and-transportation/safety-data-sheets.html>

Physical Properties

Density: < 800 kg/m³ (15 °C / 59 °F)
Kinematic Viscosity: < 2 mm²/s (25 °C / 77 °F)
Vapor Pressure: Data Not Available
Boiling Point: 260 - 320 °C / 500 - 608 °F
Melting Point: Data Not Available
Flash Point: 128.5 °C / 263.3 °F
Appearance: Colourless liquid, hydrocarbon odour

Note 1: Physical Properties are for reference only and valid as of date of this revision; see loading terminal for specific properties.

Note 2: Hazard Identification: Static accumulator; See SDS for full list of hazards and precautions.

Transhipments

Prior to arranging transhipment Charterer must agree to Owner's proposed plan. When arranged by the Owner, Owner must ensure that all transhipment vessels comply with the requirements of this cargo handling sheet.

Marpol Details

Marpol Annex: Annex I
IMO Ship Type: Double Hull vessels certified for carriage of oil
Inland Barges: Double Hull
IMO Pollution Category: Annex I
IBC 16.2.6: Not Applicable
IBC 16.2.9: Not Applicable

Pre-Wash Required: Not Applicable; wash/disposal as per Annex I

Compatibility Group: USCG compatibility group 33

Cargo Handling Requirements

N2 Purge Cargo Tanks Prior Loading:	No
N2 Blanket Required:	No
Adjacent Space Purge:	No
Loading Temperature Range:	Ambient – 30 °C / 86 °F
Transit Temperature Range:	Ambient – 30 °C / 86 °F
Unloading Temperature Range:	Ambient – 30 °C / 86 °F
Maximum Heating Coil Temperature:	Blanked off
Maximum Adjacent Temperature:	55 °C / 131 °F

Note 1: Shipping name is "Gas Oil". However, when product is shipped by Shell Chemicals, it should be treated as a water-white chemical susceptible to aromatics.

Regional Requirements

None

Tank Acceptance Requirements

All nominated shipboard cargo handling systems are to be presented clean (residual free), dry, odor free, rust free, with good gaskets, fit to load this cargo.

Maintenance of heating coils is to be verified in the ship's log. If product is to be heated, heating coils are to be confirmed leak free. If product is not heated, heating coils are to be blown clear and dried with N2, and blanked off.

Stainless Steel or Coated Tank:	Either, carrier to verify suitability of coating for product
Prior Cargo Banned:	No
Wall Wash Required:	Yes, After Aromatics only; WWT conducted with methanol except PH test, which uses DI water

Coated Tanks: WWT conducted by cargo surveyor.

Stainless Steel Tanks: verification of shipboard WWT may be accepted if below specs are met. (Send WWT Verification to the responsible Shell charterer and present to cargo surveyor and loading master at loading terminal.)

Wall Wash Test:	Specification	Standard
Appearance	Clear and free from suspended matter	ASTM D4176
Chlorides	Max 5.0 ppm	IMPCA 002-98
Hydrocarbons	= Pass	ASTM D1722
Colour Test	Max 5 Pt/Co	ASTM D1209

Additional WWT for Coated Tanks if Prior Cargo is:

Prior Cargo	Wall Wash Test:	Specification	Standard
Acrylate	PPT	> 30 minutes	ASTM D1363
Oils, Waxes, Veg Oils, Fame	NVM	100 ppm	ASTM D1353
Acids, Alkalis	PH Test	6 – 8	ASTM E70

Link to: [WWT Verification Form](#)

Safety Information and Incident Reporting

Safety Information: Refer the SDS (Safety Data Sheet) or e-SDS.

Incident Reporting: All incidents should be reported in accordance with regulations and charter party requirements.

For additional marine cargo handling advice or information, contact the regional Chemical Marine Technical Advisor.



Shell Chemical LP

PO Box 4407

Houston

Texas 77210 USA

Disclaimer

The information contained in this publication is, to the best of our knowledge, true and accurate, but any recommendations or suggestions that may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

Shell

The expression "Shell" refers to the companies of the Shell Group of companies that are engaged in the chemical businesses. Each of the companies that make up the Shell Group of companies is an independent entity and has its own separate identity.