



SHELL CARGO HANDLING SHEET

Ethylene Glycol – All Grades

Cargo Handling Sheets are for the use of vessels chartered on behalf of Shell.

Document date 26 Jan 2026

Revision no.26

Product Details

Trade Name:	Ethylene Glycol
IMO Product Name:	Ethylene Glycol
Chemical Family:	Glycols

[Link to Safety Data Sheet](#)

Physical Properties

Density:	1,113 kg/m ³ (20°C / 68°F)
Dynamic Viscosity:	16.1 mPa.s (25°C / 77°F)
Vapor Pressure:	<10 Pa (20°C / 68°F)
Boiling Point:	196°C / 385°F
Melting Point:	-13°C / 9°F
Flash Point:	115°C / 239°F
Appearance:	Slightly viscous liquid, colourless, mild odour

Note 1: Physical Properties are for reference only and valid as of date of this revision; see loading terminal for specific properties.

Note 2: Hazard Identification: See SDS for full list of hazards and precautions.

MARPOL Details

MARPOL Annex:	II
IMO Ship Type:	3; must be double hull.
Inland Barge:	Double Hull
IMO Pollution Category:	Z
IBC 16.2.6:	No
IBC 16.2.7:	No
IBC 16.2.9:	No
Pre-Wash Required:	No
Compatibility Group:	USCG compatibility group 20

Cargo Handling Requirements

N2 Purge Cargo Tanks Prior Loading:	No
N2 Blanket Required:	Yes, Product Quality requirement; Max 3% O ₂ ; see noted below and Regional Requirements
Adjacent Space Purge:	No
Loading Temperature Range:	Ambient
Transit Temperature Range:	Ambient to 40°C / 104°F
Unloading Temperature Range:	Ambient to 40°C / 104°F
Maximum Heating Coil Temperature:	Blanked off
Maximum Adjacent Temperature:	50°C / 122°F

Note 1: If vessel is required to inert tanks, then only N₂ will be accepted as an inerting medium.

Note 2: If Nitrogen blanket is in place and Carrier chooses to transship, carrier must reapply nitrogen blanket on the cargo, both on the discharging and receiving vessel, at their time, risk, and expense.

Note 3: N₂ Blanket:

a. O₂ level in tanks: Max 5% O₂ content

b. Vessel to maintain a constant nitrogen overpressure of 20 millibars or more during the voyage.

Daily Log: During the voyage the vessel shall maintain a daily log of the following and the log shall be sent to the Shell Charterer/Planner/Operator at the time of unloading. Tank pressure, O₂ level and Tank Temperature.

Regional Requirements

Note 1: Padding tanks: Unless otherwise agreed with the customer, glycol tanks will be padded as follows:

- Cross-Harbor barge
 - No requirements to blanket if load terminal to unload terminal voyage < 8 hours.
- Inter Europe Voyage ≤ 5 days.
 - EG Fibre grade - Oxygen content max 10%
 - EG Industrial and EG Antifreeze – No N₂ blanket required.
- Inter Europe Voyages > 5 days but ≤ 10 days:
 - EG Fibre grade - Oxygen content max 3%.
 - EG Industrial and EG Antifreeze - Oxygen content max 10%
- International voyages
 - EG – all Grades - Oxygen content max 3%
- FOB sales: as per receiver's requirements.
- Padding may be waived with customer's or supply manager's written agreement.

Transshipments

Prior to arranging transshipment Charterer must agree to Owner’s proposed plan. When arranged by the Owner, Owner must ensure that all transshipment vessels comply with the requirements of this cargo handling sheet.

Tank Acceptance Requirement

Banned Prior Cargo:	Stainless Steel Tanks: If prior cargo has polymerizing properties. Coated Tanks: See below appendix of banned 1 st prior cargoes. Banned prior cargoes do not apply to interline 9001 & MarineLINE 784 coated tanks.
Stainless Steel or Coated Tanks:	Stainless preferred; Zinc Coating prohibited (for US barges check with local Chem MTA).

- Note 1: Vessels offered for loading into coated tanks:
- Carrier to verify suitability of coating.
 - For newly coated tanks, either partially or fully recoated, the tanks must have carried 3 or more cargoes for a total of >90days at >90% full.
 - Tank Coating Condition Questionnaire submitted to Charterers for review prior to fixing a coated vessel.
 - Coated tanks to be in very good condition with minimal blistering or breakdown, < 0.5% total tank area.
 - All blisters to be scraped to hard coating.
 - All defects to be noted in Survey Report
 - Pipelines and fittings to be stainless steel

All nominated shipboard cargo handling systems are to be presented clean (residual free), dry, odour free, rust free, with good gaskets, fit to load this cargo.

Maintenance of heating coils is to be verified in the ship’s log. If product is to be heated, heating coils are to be confirmed leak free. If product is not heated, heating coils are to be blown clear, dried with N2, and blanked off.

Wall Wash Test Requirement

Wall Wash Required:	Yes, all conducted with Methanol except PH test, which uses DI water.
Coated Tanks:	WWT conducted by cargo surveyor
Stainless Steel tanks	Verification of shipboard WWT may be accepted if below specs are met. (Send WWT Verification to the responsible Shell charterer and present to cargo surveyor and loading master at loading terminal.) WWT Verification form is available in the supporting documents section on the CHS Website

Wall Wash Test	Specification	Standard
Appearance	Clear and free from suspended matter	ASTM D4176
Chlorides	Max 0.5 ppm	ASTM E2469
Hydrocarbons	Pass	ASTM D1722
Colour Test	Max 5 Pt/Co	ASTM D1209

Additional WWT for Coated Tanks if Prior Cargo is:

Prior Cargo	Test	Required result	Method
Acrylate	PPT	>30 minutes	ASTM D1363
Oils, Waxes, Veg Oils, Fame	NVM	100 ppm	ASTM D1353
Acids, Alkalis	PH Test	6.9 – 7.1	ASTM E70

Safety Information and Incident Reporting

Safety Information: Refer the SDS (Safety Data Sheet) or e-SDS.

Incident Reporting: All incidents should be reported in accordance with regulations and charter party requirements. For additional marine cargo handling advice or information, contact the regional Chemical Marine Technical Advisor.



Shell Trading (US) Company
 P. O. BOX 4604
 Houston,
 TX 77210-4604 USA

Disclaimer

The information contained in this publication is, to the best of our knowledge, true and accurate, but any recommendations or suggestions that may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

Shell

The expression "Shell" refers to the companies of the Shell Group of companies that are engaged in the chemical businesses. Each of the companies that make up the Shell Group of companies is an independent entity and has its own separate identity.

Banned Prior Cargoes in Coated Tanks and Potential Contamination Sources

The below products are banned as 1st prior cargo in coated tanks to load Ethylene Glycol. These banned prior cargoes do not apply to Interline 9001 coating and MarineLINE 784 coating.

Product	1 st prior cargo banned in coated tanks	Potential contamination all tanks
Acetic acid, acetic anhydride		Odour
Acetates (Ethyl, propyl, butyl)		Odour
Acrylates (ethyl, methyl, butyl, 2EH)	BANNED	UV absorbance, HC
Acrylonitrile	BANNED	UV absorbance, HC
Amyl Alcohol	BANNED	UV absorbance, HC
Amines, aliphatic		Odour
Benzene, and Mixtures containing > 0.1% benzene	BANNED	UV absorbance, HC
Brake fluids		Odour
Butanols		Odour
Carbon tetrachloride		Odour
Caustic soda		Suspended matter
Chlorinated solvents		Odour
Clean Petroleum Products (CPP)	BANNED	UV absorbance, HC
Coconut oil		Odour
Cocoa butter		Odour
Corn oil		Odour
Cotton seed oil		Odour
Cumene	BANNED	UV absorbance, HC
Dirty Petroleum Products (DPP)	BANNED	UV absorbance, HC
Dodecyl benzene	BANNED	UV absorbance, HC
Decanols	BANNED	UV absorbance, HC

Product	1 st prior cargo banned in coated tanks	Potential contamination all tanks
Ethanols		Odour
Ethanolamines (MEA, DEA, TEA)		Odour
Ethylene Dichloride		Odour
Fatty alcohols		Odour
Fish oils		Odour
Gasolines	BANNED	UV absorbance, HC
Glycol ethers (butyl, ethyl)		Odour
Isophorone	BANNED	UV absorbance, HC
Jet A1	BANNED	UV absorbance, HC
Lauryl Alcohol	BANNED	UV absorbance, HC
Luboil additives		Suspended matter, HC
MIBK		Odour
Molasses		Suspended matter, Odour
MTBE		Odour
Naphtha	BANNED	UV absorbance, HC
Nonyl Phenols (ethoxylated)	BANNED	UV absorbance, HC
Palm oils		Odour
Paraffin waxes		Suspended matter, HC
Polymerizing Products (IBC 15.13)	BANNED	UV absorbance, HC
Phenol	BANNED	UV absorbance
Phthalates	BANNED	UV absorbance, HC
Propanols		Odour
Polyols (TEG, DEG)		Odour
Phosphoric acid		Suspended matter

Product	1st prior cargo banned in coated tanks	Potential contamination all tanks
Pygas	BANNED	UV absorbance, HC
Soy bean oil		Odour
Spent glycols		Odour
Styrene	BANNED	UV absorbance, HC
Sulfonated alkyl benzenes	BANNED	UV absorbance, HC
Surfactants	BANNED	UV absorbance, HC
Sulphuric acid		Suspended matter
Tallows		Suspended matter, Odour
Tetrachloroethylene		Odour
Toluene	BANNED	UV absorbance, HC
Trichloroethylene		Odour
VAM	BANNED	UV absorbance, Odour
White spirit (kerosene, varsol)	BANNED	UV absorbance, HC
Xylene (mixed, para)	BANNED	UV absorbance, HC