



SHELL CARGO HANDLING SHEET

NEODOL 23

Cargo Handling Sheets are for the use of vessels chartered on behalf of Shell.

Document date 05 Feb 2026

Revision no.13

Product Details

Trade Name:	NEODOL 23
IMO Product Name:	NEODOL 23 (contains Dodecyl alcohol; Alcohols (C13+))
Chemical Family:	Alcohols

[Link to Safety Data Sheet](#)

Physical Properties

Density:	834 kg/m ³ (20°C / 68°F)
Dynamic Viscosity:	22 mPa.s (20°C / 68°F)
Vapor Pressure:	< 5 Pa (25°C / 77°F)
Boiling Point:	259 - 276°C / 498 - 529°F
Pour Point:	18°C / 64°F
Flash Point:	135°C / 275°F
Appearance:	Water white liquid with mild odor

Note 1: Physical Properties are for reference only and valid as of date of this revision; see loading terminal for specific properties.

Note 2: Hazard Identification: See SDS for full list of hazards and precautions.

MARPOL Details

MARPOL Annex:	II
IMO Ship Type:	2
Inland Barge:	Double Hull
IMO Pollution Category:	Y
IBC 16.2.6:	No
IBC 16.2.7:	Yes
IBC 16.2.9:	Yes
Prewash Required:	No prewash is required when unloading in accordance with this Cargo Handling Sheet, except in ports where regulation 13.7.1.4 of Annex II of MARPOL applies.

Compatibility Group: USCG compatibility group 20

Cargo Handling Requirements

N2 Purge Cargo Tanks Prior Loading:	Yes, Product Quality requirement; Max 1000 ppm (0.1%) O ₂ , see Notes and Regional Requirement below.
N2 Blanket Required:	Yes, Product Quality requirement; Max 1000 ppm (0.1%) O ₂ , see Notes and Regional Requirement below.
Adjacent Space Purge:	No
Loading Temperature Range:	35 – 50°C / 95 – 122°F
Transit Temperature Range:	35 – 50°C / 95 – 122°F
Unloading Temperature Range:	35 – 50°C / 95 – 122°F
Maximum Heating Coil Temperature:	65°C / 149°F
Maximum Adjacent Temperature:	50°C / 122°F

Note 1: If vessel is required to inert tanks, then only N₂ will be accepted as an inerting medium.

Note 2: If Nitrogen blanket is in place and Carrier chooses to transship, carrier must reapply nitrogen blanket on the cargo, both on the discharging and receiving vessel, at their time, risk, and expense.

Note 3: N₂ Blanket:

a. O₂ level in tanks: Max 1000 ppm (0.1%) O₂.

b. Vessel to maintain a constant nitrogen overpressure of 20 millibars or more during the voyage.

Daily Log: During the voyage the vessel shall maintain a daily log of the following and the log shall be sent to the Shell Charterer/Planner at the time of unloading. Tank pressure, O₂ level and Tank Temperature.

Regional Requirements

Note 1: Short voyage in Europe: may only require blanketing, however if the short voyage is part an international voyage, the short voyage must also have the tanks purged.

Note 2: Short voyage in Japan (3 days or less): Pre-load purging or padding is not required.

Transshipments

Prior to arranging transshipment Charterer must agree to Owner's proposed plan. When arranged by the Owner, Owner must ensure that all transshipment vessels comply with the requirements of this cargo handling sheet.

Tank Acceptance Requirement

Banned Prior Cargo: Yes, Styrene or any other product which can polymerize; Phosphoric acid, Sulphuric acid, and Caustic Soda.

Stainless Steel or Coated Tanks: Stainless steel only

All nominated shipboard cargo handling systems are to be presented clean (residual free), dry, odor free, rust free, with good gaskets, fit to load this cargo.

Maintenance of heating coils is to be verified in the ship's log. If product is to be heated, heating coils are to be confirmed leak free. If product is not heated, heating coils are to be blown clear, dried with N₂, and blanked off.

Wall Wash Test Requirement

Wall Wash Required: Yes, all conducted with Methanol except PH test, which uses DI water.

Stainless Steel and coated tanks Verification of shipboard WWT may be accepted if below specs are met. (Send WWT Verification to the responsible Shell charterer and present to cargo surveyor and loading master at loading terminal.) WWT Verification form is available in the supporting documents section on the [CHS Website](#)

Wall Wash Test	Specification	Standard
Appearance	Clear and free from suspended matter	ASTM D4176
Chlorides	Max 3.0 ppm	IMPCA 002-98
Hydrocarbons	Pass	ASTM D1722
Color Test	Max 10 Pt/Co	ASTM D1209

Safety Information and Incident Reporting

Safety Information: Refer the SDS (Safety Data Sheet) or e-SDS.

Incident Reporting: All incidents should be reported in accordance with regulations and charter party requirements. For additional marine cargo handling advice or information, contact the regional Chemical Marine Technical Advisor.



Shell Chemical
 PO Box 4407
 Houston
 TX77210-4604 USA

Disclaimer

The information contained in this publication is, to the best of our knowledge, true and accurate, but any recommendations or suggestions that may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

Shell

The expression "Shell" refers to the companies of the Shell Group of companies that are engaged in the chemical businesses. Each of the companies that make up the Shell Group of companies is an independent entity and has its own separate identity.