



# **SHELL CARGO HANDLING SHEET**

## **CARADOL ED56-200**

*Cargo Handling Sheets are for the use of vessels chartered on behalf of Shell.*

Document date 04 February 2026

Revision no. 12

## Product Details

Trade Names:	CARADOL ED56-200
IMO Product Name:	Polypropylene Glycol
Chemical Family:	Polyol

[Link to Safety Data Sheet](#)

## Physical Properties

Density:	1,003 kg/m <sup>3</sup> (20°C / 68°F)
Dynamic Viscosity:	500 mPa.s (20°C / 68°F)
Vapor Pressure:	<150 hPa
Boiling Point:	Not Available
Melting Point:	Not Available
Flash Point:	> 140°C / > 284°F
Appearance:	Clear, colourless, odourless

**Note 1:** Physical Properties are for reference only and valid as of date of this revision; see loading terminal for specific properties.

**Note 2:** Hazard Identification: Not classified as a physical hazard or health hazard under GHS criteria; Polymerizes exothermically with di-isocyanates at ambient temperatures. See SDS for full list of hazards and precautions.

## MARPOL Details

MARPOL Annex:	II
IMO Ship Type:	3, must be double hull
Inland Barge:	Double Hull
IMO Pollution Category:	Z
IBC 16.2.6:	No
IBC16.2.7:	No
IBC 16.2.9:	No
Pre-Wash Required:	No
Compatibility Group:	USCG compatibility group 40

## Cargo Handling Requirements

N2 Purge Cargo Tanks Prior Loading:	Not a Product Quality requirement
N2 Blanket Required:	Yes, Product Quality requirement; Max 5% O <sub>2</sub> ; See Notes below and/or Regional Requirements
Adjacent Space Purge:	No
Loading Temperature Range:	Ambient
Transit Temperature Range:	Ambient - 55 °C / 131 °F
Unloading Temperature Range:	Ambient - 55 °C / 131 °F
Maximum Heating Coil Temperature:	100 °C / 212 °F
Maximum Adjacent Temperature:	55 °C / 131 °F

## Regional Requirements

**Note1:** EU Barges – Loading Temperature Range: 35-40 °C; maintain during voyage and discharge.

**Note2:** Inter-Europe Voyages: no nitrogen blanket required for voyages < 7 days.

## Transshipments

Prior to arranging transshipment Charterer must agree to Owner's proposed plan. When arranged by the Owner, Owner must ensure that all transshipment vessels comply with the requirements of this cargo handling sheet.

### Tank Acceptance Requirement

Banned Prior Cargo:	No
Stainless Steel or Coated Tanks:	All coatings allowed except for Zinc; Carrier to verify suitability of coating.

Note 1: Vessels offered for loading into coated tanks:

- Carrier to verify suitability of coating.
- For newly coated tanks, either partially or fully recoated, the tanks must have carried 3 or more cargoes for a total of >90days at >90% full.
- Tank Coating Condition Questionnaire submitted to Charterers for review prior to fixing a coated vessel.
- Coated tanks to be in very good condition with minimal blistering or breakdown, < 0.5% total tank area.
- All blisters to be scraped to hard coating.
- All defects to be noted in Survey Report
- Pipelines and fittings to be stainless steel

All nominated shipboard cargo handling systems are to be presented clean (residual free), dry, odour free, rust free, with good gaskets, fit to load this cargo.

Maintenance of heating coils is to be verified in the ship's log. If product is to be heated, heating coils are to be confirmed leak free. If product is not heated, heating coils are to be blown clear and dried with N2, and blanked off.

### Wall Wash Test Requirement

Wall Wash Required:	Yes; all conducted with Methanol except PH test, which uses DI water.
Coated Tanks:	WWT conducted by cargo surveyor
Stainless Steel Tanks	Verification of shipboard WWT may be accepted if below specs are met. (Send WWT Verification to the responsible Shell charterer and present to cargo surveyor and loading master at loading terminal.) WWT Verification form is available in the supporting documents section on the <a href="#">CHS Website</a>

Wall Wash Test	Specification	Standard
Hydrocarbons	Pass	ASTM D1722
Chlorides	Max 1 ppm	IMPCA 002-98
Colour Test	Max 5 Pt/Co	ASTM D1209
Appearance	Clear, free of suspended matter	ASTM D4176

**Additional WWT for Coated Tanks if Prior Cargo is:**

Prior Cargo	Test	Required result	Method
Acrylate	PPT	>30 minutes	ASTM D1363
Oils, Waxes, Veg Oils, Fame	NVM	100 ppm	ASTM D1353
Acids, Alkalis	PH Test	6.9 - 7.1	ASTM E70

**Safety Information and Incident Reporting**

**Safety Information:** Refer the SDS (Safety Data Sheet) or e-SDS.

**Incident Reporting:** All incidents should be reported in accordance with regulations and charter party requirements. For additional marine cargo handling advice or information, contact the regional Chemical Marine Technical Advisor.



Shell Chemical LP  
PO Box 4407  
Houston  
Texas 77210 - USA

**Disclaimer**

The information contained in this publication is, to the best of our knowledge, true and accurate, but any recommendations or suggestions that may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

**Shell**

The expression "Shell" refers to the companies of the Shell Group of companies that are engaged in the chemical businesses. Each of the companies that make up the Shell Group of companies is an independent entity and has its own separate identity.