



# **SHELL CARGO HANDLING SHEET**

## **CARADOL SC48-08**

*Cargo Handling Sheets are for the use of vessels chartered on behalf of Shell.*

Document date 04 February 2026  
Revision no. 17

Document date 27 January 2026  
Revision no. 17

## Product Details

|                   |                                        |
|-------------------|----------------------------------------|
| Trade Names:      | CARADOL SC48-08                        |
| IMO Product Name: | Glycerol, Propoxylated and Ethoxylated |
| Chemical Family:  | Polyol                                 |

[Link to Safety Data Sheet](#)

## Physical Properties

|                    |                                       |
|--------------------|---------------------------------------|
| Density:           | 1,019 kg/m <sup>3</sup> (20°C / 68°F) |
| Dynamic Viscosity: | 760 mPa.s (20°C / 68°F)               |
| Vapor Pressure:    | <10 hPa                               |
| Boiling Point:     | Not Available                         |
| Melting Point:     | Not Available                         |
| Flash Point:       | > 200°C / > 392°F                     |
| Appearance:        | Clear, colourless liquid              |

**Note 1:** Physical Properties are for reference only and valid as of date of this revision; see loading terminal for specific properties.

**Note 2:** Hazard Identification: Not classified as a physical hazard or health hazard under GHS criteria; Polymerizes exothermically with di-isocyanates at ambient temperatures. See SDS for full list of hazards and precautions.

## MARPOL Details

|                         |                             |
|-------------------------|-----------------------------|
| MARPOL Annex:           | II                          |
| IMO Ship Type:          | 3, must be double hull      |
| Inland Barge:           | Double Hull                 |
| IMO Pollution Category: | Z                           |
| IBC 16.2.6:             | No                          |
| IBC16.2.7:              | No                          |
| IBC 16.2.9:             | No                          |
| Pre-Wash Required:      | No                          |
| Compatibility Group:    | USCG compatibility group 40 |

## Cargo Handling Requirements

|                                     |                                                                                                                                         |
|-------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------|
| N2 Purge Cargo Tanks Prior Loading: | Not a Product Quality requirement                                                                                                       |
| N2 Blanket Required:                | Yes, Product Quality requirement; Max 5% O <sub>2</sub> , see Notes below and Regional Requirements.                                    |
| Adjacent Space Purge:               | No                                                                                                                                      |
| Loading Temperature Range:          | Ambient - 40 °C / 104 °F                                                                                                                |
| Transit Temperature Range:          | 40 - 55 °C / 104 - 131 °F (International)<br>35 - 40 °C / 104 °F (Discharge location Rotterdam)<br>Ambient - 45 °C / 113 °F (EU Barges) |
| Unloading Temperature Range:        | 40 - 55 °C / 104 - 131 °F (International)<br>38 - 40 °C / 104 °F (Discharge location Rotterdam)<br>Ambient - 50 °C / 122 °F (EU Barges) |
| Maximum Heating Coil Temperature:   | 100 °C / 212 °F                                                                                                                         |
| Maximum Adjacent Temperature:       | 55 °C / 131 °F                                                                                                                          |

**Note 1:** If Nitrogen blanket is in place and Carrier chooses to transship, carrier must reapply nitrogen blanket on the cargo, both on the discharging and receiving ship, at their time, risk, and expense.

**Note 2:** For discharge location Rotterdam, vessel should not discharge cargo at temperature higher than 40 °C / 104 °F, to meet receiving Customer's requirement. Slow pumping rate / additional ROB may be experienced.

**Note 3:** N2 Blanket Guidance:

- a. O<sub>2</sub> level in tanks to be maintained below 5% O<sub>2</sub>, See Regional Requirements
- b. Vessel to maintain a constant nitrogen overpressure of 20 millibars or more during the voyage
- c. **DAILY LOG:** During the voyage the vessel shall record the following at least once a day and the record shall be sent to the Shell Charterers/Planners after the completion of unloading.
  1. Tank pressure 2. O<sub>2</sub> level 3. Tank Temperature

## Regional Requirements

**Note 1:** On voyages between Saraya Singapore and Rotterdam, vessel should discharge at no higher than 40 °C / 104 °F to comply with receiving facility requirements. Slow pumping rate / additional ROB may be experienced.

**Note 2:** Inter-Europe Voyages: no N2 blanket required for voyages < 3 days.

**Note 3:** Barge voyages in Europe - With same prior cargo of SC48-08, tanks can be loaded without cleaning.

## Transshipments

Prior to arranging transshipment Charterer must agree to Owner's proposed plan. When arranged by the Owner, Owner must ensure that all transshipment vessels comply with the requirements of this cargo handling sheet.

### Tank Acceptance Requirement

|                                  |                                                                                 |
|----------------------------------|---------------------------------------------------------------------------------|
| Banned Prior Cargo:              | No                                                                              |
| Stainless Steel or Coated Tanks: | All coatings allowed except for Zinc; Carrier to verify suitability of coating. |

Note 1: Vessels offered for loading into coated tanks:

- Carrier to verify suitability of coating.
- For newly coated tanks, either partially or fully recoated, the tanks must have carried 3 or more cargoes for a total of >90days at >90% full.
- Tank Coating Condition Questionnaire submitted to Charterers for review prior to fixing a coated vessel.
- Coated tanks to be in very good condition with minimal blistering or breakdown, < 0.5% total tank area.
- All blisters to be scraped to hard coating.
- All defects to be noted in Survey Report
- Pipelines and fittings to be stainless steel

All nominated shipboard cargo handling systems are to be presented clean (residual free), dry, odour free, rust free, with good gaskets, fit to load this cargo.

Maintenance of heating coils is to be verified in the ship's log. If product is to be heated, heating coils are to be confirmed leak free. If product is not heated, heating coils are to be blown clear and dried with N2, and blanked off.

### Wall Wash Test Requirement

|                       |                                                                                                                                                                                                                                                                                                                  |
|-----------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Wall Wash Required:   | Yes; all conducted with Methanol except PH test, which uses DI water.                                                                                                                                                                                                                                            |
| Coated Tanks:         | WWT conducted by cargo surveyor                                                                                                                                                                                                                                                                                  |
| Stainless Steel Tanks | Verification of shipboard WWT may be accepted if below specs are met. (Send WWT Verification to the responsible Shell charterer and present to cargo surveyor and loading master at loading terminal.) WWT Verification form is available in the supporting documents section on the <a href="#">CHS Website</a> |

| Wall Wash Test | Specification                           | Standard     |
|----------------|-----------------------------------------|--------------|
| Hydrocarbons   | Pass                                    | ASTM D1722   |
| Chlorides      | Max 5 ppm                               | IMPCA 002-98 |
| Colour Test    | Max 5 Pt/Co                             | ASTM D1209   |
| Appearance     | Clear, free of suspended matter & Odour | ASTM D4176   |
| Permanganate   | >30 minutes                             | ASTM D1363   |

**Additional WWT for Coated Tanks if Prior Cargo is:**

| Prior Cargo                 | Test    | Required result | Method     |
|-----------------------------|---------|-----------------|------------|
| Oils, Waxes, Veg Oils, Fame | NVM     | 100 ppm         | ASTM D1353 |
| Acids, Alkalies             | PH Test | 6.9 – 7.1       | ASTM E70   |

**Safety Information and Incident Reporting**

**Safety Information:** Refer the SDS (Safety Data Sheet) or e-SDS.

**Incident Reporting:** All incidents should be reported in accordance with regulations and charter party requirements.

For additional marine cargo handling advice or information, contact the regional Chemical Marine Technical Advisor.



Shell Chemical LP  
PO Box 4407  
Houston  
Texas 77210 - USA

**Disclaimer**

The information contained in this publication is, to the best of our knowledge, true and accurate, but any recommendations or suggestions that may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

**Shell**

The expression "Shell" refers to the companies of the Shell Group of companies that are engaged in the chemical businesses. Each of the companies that make up the Shell Group of companies is an independent entity and has its own separate identity.